

## Prediction of Permeability for a composite of bisphen\_dimeth\_carbonate and butylene\_isophthalate

Suman Patra<sup>1</sup>, Susant K. Biswal<sup>2</sup>

<sup>1</sup>190705100003@cutm.ac.in, <sup>2</sup>dr.skbiswal@cutm.ac.in

Centurion University of Technology and Management, Odisha, India

**Abstract:** A computational study has been done to predict Permeability of a polymer composite consisting of bisphen\_dimeth\_carbonate and butylene\_isophthalate. Synthia module of Biovia Materials Studio software was used to predict Glass transition temperature, Density, Oxygen permeability, Nitrogen permeability and Carbon dioxide permeability of the composite.

**Objective:** In this study the effect of mixing of bisphen\_dimeth\_carbonate and butylene\_isophthalate on the following properties have been predicted.

- a. Glass transition temperature
- b. Density
- c. Oxygen permeability
- d. Nitrogen permeability
- e. Carbon dioxide permeability

The weight fractions of the monomers were varied in the range of 0 to 1.

Software used: Synthia module of Biovia Materials Studio software (Dassault Systemes, France) was used for the study.

**Results and Discussion:** The effect of weight fraction of bisphen\_dimeth\_carbonate (Monomer 1) on the Permeability of the composite has been presented in Table 1. The predicted properties of the composite for 0, 0.5 and 1.0 weight fractions of bisphen\_dimeth\_carbonate have been summarized in Table 1. The rate of change for the properties have been summarized in Table 2.

Table 1. Properties of composite of bisphen\_dimeth\_carbonate and butylene\_isophthalate

Property		Results for		
Name	Unit	0.0 weight fraction of bisphen_dimeth_carbonate	0.5 weight fraction of bisphen_dimeth_carbonate	1.0 weight fraction of bisphen_dimeth_carbonate
Glass transition temperature	oC	308.194	362.127	414.398
Density	kg per	1.237	1.205	1.174