

Prediction of Optical, electrical and thermal properties for a composite of tetmeth_bisphen_carbonate and butylene_terephthalate

Arghyarupa Dhal¹, Dr Tapan Dash²

¹190705120010@cutm.ac.in, ²tapan.dash@cutm.ac.in

Centurion University of Technology and Management, Odisha, India

Abstract: A computational study has been done to predict Optical, electrical and thermal properties of a polymer composite consisting of tetmeth_bisphen_carbonate and butylene_terephthalate. Synthia module of Biovia Materials Studio software was used to predict Refractive index, Volume resistivity, Dielectric constant, Coefficient of volumetric thermal expansion and Thermal conductivity of the composite.

Objective: In this study the effect of mixing of tetmeth_bisphen_carbonate and butylene_terephthalate on the following properties have been predicted.

- Refractive index
- Volume resistivity
- Dielectric constant
- Coefficient of volumetric thermal expansion
- Thermal conductivity

The weight fractions of the monomers were varied in the range of 0 to 1.

Software used: Synthia module of Biovia Materials Studio software (Dassault Systemes, France) was used for the study.

Results and Discussion: The effect of weight fraction of tetmeth_bisphen_carbonate (Monomer 1) on the Optical, electrical and thermal properties of the composite has been presented in Table 1. The predicted properties of the composite for 0, 0.5 and 1.0 weight fractions of tetmeth_bisphen_carbonate have been summarized in Table 1. The rate of change for the properties have been summarized in Table 2.

Table 1. Properties of composite of tetmeth_bisphen_carbonate and butylene_terephthalate

Property		Results for		
Name	Unit	0.0 weight fraction of tetmeth_bisphen_carbonate	0.5 weight fraction of tetmeth_bisphen_carbonate	1.0 weight fraction of tetmeth_bisphen_carbonate
Refractive index	0	1.544	1.559	1.572
Volume resistivity	Ohm-metre	5913188000000000.000	142694700000000000.000	324667800000000000.000